



1. PRODUCT NAME

**Ultra-Shield Rubberized Cement**

2. MANUFACTURER

GMX, Inc.  
3800 E. 91st Street  
Cleveland, OH 44105  
Phone: 866-228-7743  
Fax: 216-430-3500

3. PRODUCT DESCRIPTION

Ultra-Shield Rubberized Cement is a fiber-reinforced, asbestos-free roof cement which is rubber-modified to improve its performance. It cures to a flexible, tough, waterproof seal.

3. PRODUCT ADVANTAGES

**One-Step Labor Savor** - Ultra-Shield Rubberized Cement comes ready to use. No mixing, thinning, heating or stirring are required. Generally, Ultra-Shield Rubberized Cement requires no membrane reinforcement or priming, and it is compatible with both tar and asphalt roof surfaces.

**Multi-Purpose Application** - Ultra-Shield Rubberized Cement is ideal for metalwork flashing repairs, metal roof surface repairs, blisters, splits and coping stone joints.

4. USES

Ultra-Shield Rubberized Cement is recommended for the repair of holes, tears, rips, etc. in asphalt or composition roofing. It can also be used to seal flashings, lap seams, vents, gutters and skylights. It is the ideal sealant for dissimilar construction materials (i.e. materials with differing coefficients of expansion/contraction).

5. APPLICATION

Trowel apply to clean, dry surfaces only. On flashing applications, allow the material to set for a few moments before positioning the flashing materials. Ultra-

Shield Rubberized Cement is designed for use without reinforcing fabric. If reinforcing fabric is desired, apply a base coat of cement, embed a layer of glass or polyester membrane into the base coat, and top dress with an additional layer of cement.

6. QUALITY AND CONSISTENCY - ISO 9001

Ultra-Shield Rubberized Cement is manufactured to the highest quality standards and in accordance with ISO 9001 requirements. ISO certification ensures that every gallon manufactured meets the highest quality control standards in the industry and provides outstanding performance in the field.

GMX materials are produced in and shipped from our plant in Cleveland, OH. For the name and number of the nearest GMX representative, call us at 866-228-7743. Our representatives can provide pricing and put you in contact with our nearest stocking distributor.

7. TECHNICAL SERVICES

Your local GMX representative is available to assist you in selecting the appropriate product and to provide on-site application assistance. For further information, please contact our Technical Service Dept. at 866-228-7743.

TECHNICAL DATA - Ultra-Shield Rubberized Cement	
Sag @ 77°F (25°C), 1/4" thick (.64 cm) ASTM D 4586	None
Flash Point ASTM D 93	102°F (38°C)
Non-volatile (%) ASTM D 4586	Typical 75%
Elongation, 14-day cure @ 77°F (25°C) ASTM D 412	800% min.
Viscosity	400,000-600,000 cPs
Density	8.0 lbs./gal (.96 g/cm3)
VOC Status (ASTM D 3960)	max 275 g/l

**TROWEL-APPLIED**  
Cement